



**Y350**

**Product Features:**

- 6.3-oz, 100% performance polyester interlock with wicking technology
- No Bleed Fabric (NBF) created with a unique cationic dye process for easy printing
- Side seamed

Youth sizes:

XS(2-4) S(6-8), M(10-12), L(14-16), XL(18-20)

**Icons/Fabric Features:**



**Available Colours and PMS Colours**

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference



Due to the nature of polyester, special care must be taken throughout the decoration process.

## Y350 - ATC™ Pro Team Short Sleeve Youth Tee

### GARMENT MEASUREMENTS

Size	XS	S	M	L	XL
Chest - <i>Half Measure</i>	15 1/4"	16"	17"	18"	19 1/2"
Chest - <i>Full Measure</i>	30 1/2"	32"	34"	36"	39"
Body Length from HPS	20"	21 1/2"	23"	25"	27"
Sleeve Length-CB	12 1/2"	13 1/2"	14 1/2"	15 1/2"	16 1/2"

### YOUTH General Sizing Guide

Size	XS	S	M	L	XL
Numeric Size	2-4	6-8	10-12	14-16	18-20
Chest	24"-26"	26"-28"	28"-30"	30"-32"	32"-35"
Waist	22 1/2"-23 1/2"	23"-24 1/2"	24 1/2"-25 1/2"	25 1/2"-27"	27"-29"
Sleeve Length-CB	24"-25"	25"-26"	26"-27 1/2"	27 1/2"-29"	29 1/2"-31"



## DECORATING INSTRUCTIONS FOR NO BLEED POLYESTER FABRICS

Due to the nature of polyester, special care must be taken throughout the decoration process.

Here are some tips to effectively decorate our no bleed performance products.

- Garment temperature must not exceed 320°F or 160°C. Exceeding this temperature will cause the fabric to shrink, become wavy or cause dye migration.
- Dryer temperature and belt speeds must be changed accordingly for polyester fabric.
- If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.
- **Screen Printing:** These garments require the use of poly inks that cures at a lower temperature. Please consult your ink supplier for more information.
- Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer's fold may cause the fabric and applied ink to stick together.
- **Heat Transfers:** If you heat press these garments, you must adjust the time, temperature and pressure. Failure to do so may damage the fabric as stated above.
- **Sublimation Printing:** This process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.
- A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on performance fabrics.